

Amendment/Reply

Applicant: Hong-Jyh Li

Serial No.: 10/816,503

Filed: April 1, 2004

Docket No.: 2004P51130US/1331.228.101

Title: PLASMA ION IMPLEMENTATION SYSTEM

IN THE CLAIMS

Please amend claims 4, 8, 10, 11, 14, 16, 17, 20, 23, 25, and 28-31 as follows:

1. (Previously Presented) A plasma ion implantation system comprising:
a vacuum chamber;
a plasma generator configured to generate ions in the vacuum chamber;
a sample holder inside the vacuum chamber; and
a voltage source configured to provide a bias voltage between the sample holder and the vacuum chamber to attract ions to implant in a high-k dielectric layer of a sample positioned on the sample holder,
wherein the high-k dielectric layer has a k value greater than 9.
2. (Original) The plasma ion implantation system of claim 1, wherein the ions comprise N.
3. (Original) The plasma ion implantation system of claim 1, wherein the ions comprise one of F, Si, O, Hf, Zr, Ti, Ta, Y, V, Sc, Ba, Sr, Ru, B, Al, Ga, In, Ge, C, P, As, and Sb.
4. (Currently Amended) The plasma ion implantation system of claim 1, wherein the voltage source comprises a constant DC voltage source.
5. (Original) The plasma ion implantation system of claim 1, wherein the voltage source comprises an AC voltage source.
6. (Original) The plasma ion implantation system of claim 1, further comprising:
a vacuum pump for providing a specified pressure in the vacuum chamber.

Amendment/Reply

Applicant: Hong-Jyh Li

Serial No.: 10/816,503

Filed: April 1, 2004

Docket No.: 2004P51130US/I331.228.101

Title: PLASMA ION IMPLEMENTATION SYSTEM

7. (Original) The plasma ion implantation system of claim 1, further comprising:
a gas feed system for providing a gas to the vacuum chamber from which the plasma generator generates the ions.
8. (Currently Amended) A plasma ion implantation system comprising:
a vacuum chamber;
a vacuum pump configured to set a pressure in the vacuum chamber;
a gas feed system configured to provide a gas to the vacuum chamber;
a plasma generator configured to generate ions from the gas;
a sample holder configured to hold a sample to be implanted; and
a constant DC voltage source configured to accelerate positive ions toward a high-k dielectric layer of the sample to implant the positive ions in the high-k dielectric layer and to repel negative ions from the sample,
wherein the high-k dielectric layer has a k value greater than 9.
9. (Original) The plasma ion implantation system of claim 8, wherein the DC voltage source is coupled to the sample holder and the vacuum chamber.
10. (Currently Amended) The plasma ion implantation system of claim 8, wherein the positive ions comprise N.
11. (Currently Amended) The plasma ion implantation system of claim 8, wherein the positive ions comprise one of F, Si, O, Hf, Zr, Ti, Ta, Y, V, Sc, Ba, Sr, Ru, B, Al, Ga, In, Ge, C, P, As, and Sb.
12. (Previously Presented) The plasma ion implantation system of claim 8, wherein the high-k dielectric layer comprises one of HfO₂, HfSiO, ZrO₂, ZrSiO, Ta₂O₅, La₂O₃, and Al₂O₃.

Amendment/Reply

Applicant: Hong-Jyh Li

Serial No.: 10/816,503

Filed: April 1, 2004

Docket No.: 2004P51130US/I331.228.101

Title: PLASMA ION IMPLEMENTATION SYSTEM

13. (Original) The plasma ion implantation system of claim 8, wherein the sample comprises a buffer layer proximate the high-k dielectric layer.
14. (Currently Amended) The plasma ion implantation system of claim 13, wherein the DC voltage source is configured to accelerate positive ions toward the buffer layer of the sample to implant the positive ions in the buffer layer.
15. (Original) The plasma ion implantation system of claim 14, wherein the buffer layer comprises one of TiN, HfN, TaN, ZrN, LaN, SiN, and TiSi.
16. (Currently Amended) A plasma ion implantation system comprising:
a vacuum chamber;
a vacuum pump configured to set a pressure in the vacuum chamber;
a gas feed system configured to provide a gas to the vacuum chamber;
a plasma generator configured to generate ions from the gas, the ions comprising one of F, Si, O, Hf, Zr, Ti, Ta, Y, V, Sc, Ba, Sr, Ru, B, Al, Ga, In, Ge, C, P, As, and Sb;
a sample holder configured to hold a sample to be implanted; and
a voltage source configured to accelerate positive ions toward a first high-k dielectric layer of the sample to implant the positive ions in the first high-k dielectric layer and to repel negative ions from the sample,
wherein the first high-k dielectric layer has a k value greater than 9.
17. (Currently Amended) The plasma ion implantation system of claim 16, wherein the voltage source is configured to accelerate positive ions toward a second high-k dielectric layer of the sample adjacent the first high-k dielectric layer to implant the positive ions in the second high-k dielectric layer.

Amendment/Reply

Applicant: Hong-Jyh Li

Serial No.: 10/816,503

Filed: April 1, 2004

Docket No.: 2004P51130US/1331.228.101

Title: PLASMA ION IMPLEMENTATION SYSTEM

18. (Original) The plasma ion implantation system of claim 17, wherein the first high-k dielectric layer comprises one of HfSiO_x and ZrSiO_x .

19. (Previously Presented) The plasma ion implantation system of claim 18, wherein the second high-k dielectric layer comprises one of HfO_2 , HfSiO_x , ZrO_2 , ZrSiO_x , Ta_2O_5 , La_2O_3 , and Al_2O_3 .

20. (Currently Amended) The plasma ion implantation system of claim 19, wherein the voltage source is configured to accelerate positive ions toward a buffer layer of the sample adjacent the second high-k dielectric layer to implant the positive ions in the buffer layer.

21. (Original) The plasma ion implantation system of claim 20, wherein the buffer layer comprises at least one of TiN, HfN, TaN, ZrN, LaN, SiN, and TiSi.

22. (Original) The plasma ion implantation system of claim 20, wherein the buffer layer comprises a stack of layers.

23. (Currently Amended) The plasma ion implantation system of claim 21, wherein the voltage source is a constant DC voltage source.

24. (Original) The plasma ion implantation system of claim 21, wherein the voltage source is an AC voltage source.

25. (Currently Amended) A method of implanting ions in a sample, the method comprising:
positioning a sample comprising a high-k dielectric layer on a sample holder in a vacuum chamber, the high-k dielectric layer having a k value greater than 9;
providing a gas to the vacuum chamber;
setting a pressure in the vacuum chamber;
generating a plasma in the vacuum chamber from the gas; and

Amendment/Reply

Applicant: Hong-Jyh Li

Serial No.: 10/816,503

Filed: April 1, 2004

Docket No.: 2004P51130US/I331.228.101

Title: PLASMA ION IMPLEMENTATION SYSTEM

accelerating positive ions in the plasma toward the sample to implant the positive ions in the high-k dielectric layer while repelling negative ions from the sample.

26. (Original) The method of claim 25, wherein generating a plasma comprises generating a plasma comprising N ions.
27. (Original) The method of claim 25, wherein generating a plasma comprises generating a plasma comprising one of F, Si, O, Hf, Zr, Ti, Ta, Y, V, Sc, Ba, Sr, Ru, B, Al, Ga, In, Ge, C, P, As, and Sb ions.
28. (Currently Amended) The method of claim 25, wherein accelerating positive ions in the plasma toward the sample comprises biasing the sample with a constant DC voltage.
29. (Currently Amended) The method of claim 25 wherein accelerating positive ions in the plasma toward the sample comprises biasing the sample with an AC voltage.
30. (Currently Amended) The method of claim 25, wherein accelerating positive ions in the plasma toward the sample to implant the positive ions in the sample comprises implanting the positive ions having a dose ~~within a range of~~ greater than 1×10^{13} ions/cm² ~~and to less than~~ 1×10^{16} ions/cm².
31. (Currently Amended) The method of claim 25, wherein accelerating positive ions in the plasma toward the sample to implant the positive ions in the sample comprises accelerating the positive ions to have an implant energy ~~within a range of~~ greater than 5eV and to less than 10keV.